

# SealGuard II

Dual Component, Highly Reactive, Early Strength, Water Control Grout

## Applications

For high flowing water control and I&I applications in manholes, vaults, and other concrete brick or stone structures above or below grade.

## Advantages

- Extremely Fast Reaction Time
- Rapid Sealing
- High Early Strength
- Great Migration Into Fractures
- Will Not Wash Out
- Patented Back Flow Prevention

## Storage

Do not crush containers.

Avoid contact with moisture.

Store under 80°F 27°C.

**Product has a 2 year shelf life in unopened containers.**

## Packaging

600 mL Tube Sets

5 Gallon pails

55 Gallon Drums

## Transport

US D.O.T. Unregulated Class-55

## Customer Support

866-625-4550

info@SealGuardInc.com



## Uncured Physical Properties

|                          |                |                |
|--------------------------|----------------|----------------|
| Shrinkage (-20° F)       | 0% 1 Day       | ASTM D-2126    |
| Viscosity (68° F)        | 200 cps A-side | 300 cps B-side |
| Specific Gravity (60° F) | 1.23 A-side    | 1.04 B-side    |
| Percent Solids           | 100%           |                |
| Color                    | Amber          |                |
| Solvents                 | None           |                |

## Cured Material - Physical Properties

|                     |         |             |
|---------------------|---------|-------------|
| Density – Free Rise | 08 PCF  | ASTM D-1622 |
| Compressive         | 900 psi | ASTM D-1621 |
| Tensile             | 200 psi | ASTM D-638  |
| Shear               | 190 psi | ASTM D-732  |

**\*\* Thoroughly read all instructions and cautions prior to use \*\***